

See
D1

--17. A method of manufacturing a semiconductor integrated circuit device, comprising the steps of:

- (a) providing a silicon wafer covered with an insulating film whose main surface is mainly formed of silicon oxide;
- (b) cleaning the surface of said silicon wafer by a sheet-by-sheet manner with use of a processing solution containing hydrogen peroxide, hydricid fluoride salt, and water;
- (c) removing said insulating film after said step (b) thereby to expose the surface of said silicon wafer; and
- (d) subjecting said silicon wafer to a heat-treatment after said step (c) thereby to form a gate oxide film over said silicon wafer.

B1

18. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein the hydricid fluoride salt included in said processing solution is ammonium fluoride.

19. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein the hydricid fluoride salt included in said processing solution is tetraalkyl ammonium fluoride.

20. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein said processing solution includes HF and HF_2^- as etching seeds of silicon oxide.

21. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein concentration of said hydricid fluoride salt in said processing solution is in a range of about 0.1 to 3 mol/l.

22. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein said processing solution further includes a surfactant.

23. A method of manufacturing semiconductor integrated circuit device according to claim 17, further comprising a step of cleaning the surface of said silicon wafer during ultrasonic vibration of said processing solution.

24. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein, after said step (c), the heat treatment in said step (d) is performed without exposing said silicon wafer to atmosphere.

Sub
C1

25. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein said cleaning is performed at a temperature as low as 40°C.

26. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein the processing solution has a pH in a range of 6 to 11.

27. A method of manufacturing a semiconductor integrated circuit device according to claim 26, wherein the processing solution further includes a surfactant.

B1
Cmt,

28. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein the heat treatment forming the gate oxide film, in step (d), is performed in a mixed atmosphere of water and oxygen, at a temperature in a range of 800°-900°C.

29. A method of manufacturing a semiconductor integrated circuit device according to claim 17, wherein after removing said insulating film in step (c), the silicon wafer is dried prior to step (d).

30. A method of manufacturing a semiconductor integrated circuit

B1
cont. device according to claim 29, wherein after said drying the silicon wafer is immediately transferred to a chamber for the step (d) of subjecting the silicon wafer to the heat-treatment thereby to form the gate oxide film.--
